

BATHGATE

SILICA SAND

TOP DRESSING

*A heat-treated Top Dressing
screened through a 3 mm square mesh*

PRODUCT INFORMATION

ISSUE NO 3.07

TYPICAL GRADINGS

USGA

TD3

TD4

TD5

CLASSIFICATION	SIEVE SIZE MM	% RETAINED	% RETAINED	% RETAINED	% RETAINED
FINE GRAVEL	4.00-2.00	0.5	0.9	0.9	0.9
VERY COARSE SAND	2.00-1.00	1.3	1.8	1.7	1.4
COARSE SAND	1.00-.050	11.3	21.3	8.2	7.8
MEDIUM SAND	0.50-0.25	71.2	65.3	58.5	53.5
FINE SAND	0.25-0.15	14.2	9.7	28.6	33.8
VERY FINE SAND	0.15-0.053	1.4	1.1	2.0	2.5
CLAY/ SILT	<0.053	0.1	TRACE	0.1	0.1
Ph		6.8	7.3	6.8	7.3
FREE LIME CONTENT				TRACE	TRACE

Bathgate Silica Sand Limited

Arclid Quarry, Congleton Road, Sandbach, Cheshire. CW11 4SN

Telephone : 01270 762828 Fax : 01270 760557

www.bathgatesilica.co.uk

Silica sand is a natural raw material. All data is to be considered as indicative. Each customer is encouraged to determine the suitability of our product for their own application. Upon simple request we will be pleased to discuss tolerances on the above product data. Sales and supplies will always be according to our general sales conditions

All systems operate under the auspices of BS EN ISO 9001:2000 and the company is registered with the British Standards Institute as complying with these requirements



Certification No. FM 01396